

# TECHNOFACADE heat-insulating mineral wool boards

Production in compliance with the standard EN 13162.

MW-EN 13162-T5- DS (70,-)-DS(23,90)- CS(10)40-TR15-PL(5)400 -WS-WL(P)-MU1- RtF: A1

MANUFACTURER: LLC «Plant «TECHNO» 18018 Ukraine, Cherkassy, Rizdvyana Street 300.

ORIGIN: Ukraine



# Non-flammable stone wool slabs made of basaltic and gabbroic rocks

### **Product Description**

TECHNOFACADE is non-flammable, hydrophobizated heat- and sound-insulating slabs made of mineral wool based on the basalt group rocks.

## Scope of application:

TECHNOFACADE slabs are intended for use in civil and industrial construction as thermal and sound insulation in systems of external wall insulation with a protective and decorative layer of fine plaster.

#### Storage:

Slabs should be stored packed and stacked on pallets divided by types and sizes. During the entire storage period, the material must be protected from atmospheric precipitation. The height of the stack of slabs should not exceed 3 m upon storage.

### **Packaging Details:**

Polyethylene shrink wrap is used for packaging. The method of wrapping and fixing a packaging material must ensure the reliable and strong packaging of slabs, their protection during loading and unloading operations, transportation and storage.

#### **Technical Characteristics**

ESSENTIAL CHARACTERISTICS	PERFORMANCE	HARMONIZED TECHNICAL SPECIFICATION
Declared thermal conductivity at 10 °C, λD, W/m*K	0,039	EN 13162:2012 + A1:2015
Limit deviations length/width, mm	±2/±1,5 %	
Limit deviations of thickness, mm	T5	
Thickness, (with increments of 10 mm), mm	40-160	
Deviation from squareness, mm/m	< 5	
Deviation from flatness, mm	< 6	
Compressive stress at 10% deformation, kPa	CS(10)40	
Tensile strength perpendicular to faces, kPa	TR15	
Point Load, N	PL(5)400	
Dimensional stability, %: - at specified temperature - under specified temperature (23oC) and humidity	DS(70,-) less than 1	
conditions (90%R.H.)	DS(23,90) less than 1	
Reaction to fire, euroclass	A1	
Water Absorption during Short/	WS less than 1	
Longterm Immersion kg/m²	WL(P) less than 3	
Water vapour transmission, MU	MU1	
Dangerous substances	Does not include dangerous substances	